

● Specifications of single cell

Type

Nominal Voltage

Nominal Capacity

Average Weight

Diameter

Height

Charging Method: (20°C)

Standard Charge,

Quick Charge

Max Overcharge Current

Trickle Current

Discharge

Operating Temperature(reference only):

Storage

Discharge:

Standard Charge

Fast Charge

Sealed Ni-MH button cell

1.2V (Single cell, Series voltage is 1.2 * N)

110mAh

4.5g

Ø15.2mm

7.8mm (Max.)

Charge with 0.1C (11mA) for 14-16 hours

Charge with 0.2C (22mA) for 7-8 hours

11mA(No longer than 48 hours)

3-5.5 mA

22mA

55mA (Max.)





-10°C~35°C

-10°C~65°C


0°C~45°C

10°C~35°C

● Typical characteristics



● Single battery draw



● **Performance**

Testing Item	Testing Conditions				Standard
Standard Testing Condition	The test is carried out with new batteries (within a month after delivery). ambient conditions: Temperature: 20±5℃ Humidity: 65±20% Tolerances ±5‰ for voltage and current				
Normal Charge	charging at a constant current of 0.1C for 16h. Prior to charging, the cell shall have been discharged at a constant current of 0.2C, down to a final voltage of 1.0V/cell *N.				
(1)OpenCircuit Voltage	Test within 14 days after standard charge				≥1.25V *N
(2)Capacity	The cell shall be charged. After charging, the cell shall be stored for 1h, then the cell shall have been discharged at a constant current of 0.2C, down to a final voltage of 1.0V/cell *N. 5 cycles are permitted for this test.				≥300min
(3)Overcharge	Prior to this test, the cell shall be discharged. The cell shall then be charged at a constant current of 0.1C for 48h. After this charging operation, the cell shall be stored 1h, The cell shall then be discharged at a constant current of 0.2C to a final voltage of 1.0V/cell *N.				≥255min
(4)Charge retention	The charged cell is stored for 28 days. And the discharge time is measured at normal discharge.				≥225min
(5)Life expectancy (IEC cycle)	Cycle	Charge	Rest	Discharge	≥500 th cycle
	1	0.1C x 960min	None	0.25C x140 min	
	2-48	0.25C x190 min	None	0.25C x140 min	
	49	0.25C x190 min	None	0.25C to 1.0V/cell *N	
	50	0.1C x 960min	1-4h	0.2C to 1.0V/cell *N	
Cycles 1 to 50 shall be repeated until the discharge duration on any 50th cycle becomes less than 3h. At this stage, a repeat capacity measurement as specified for cycle 50 shall be carried out. The endurance test is considered complete when two such successive capacity cycles give a discharge duration of less than 3h. [IEC61951-2:(2003)7.4.1.1]					
(6)Storage	Standard Charged as (1) condition and stored for 12 months under 20℃±5℃, then tested as (4) condition.				≥240min

● **Note**

- 1) Do not dispose of cell into fire or be dismantled under any condition.
- 2) Do not mix different cell types and capacities in the same battery assembly.
- 3) Charge and discharge under specified ambient temperature recommended to HISUN specification.
- 4) Short circuit leading to cell venting must be avoided.
- 5) Never solder onto cell directly. Cell reversal should be avoided.
- 6) Use batteries in extreme condition may affect the service life, such as: extreme temperature, deep cycle, extreme overcharge and over discharge.
- 7) Batteries should be stored in a cool dry place.
- 8) Up to three full cycles of charge /discharge after long-termed storage may need to obtain highest capacity.
- 9) Quality assurance period: 12 months